


Evidence of performance
Airborne sound insulation of building components

Test Report

No. GLA-1288.8/16Client**PRESS GLASS S.A.**Nowa Wieś
ul. Kopalniana 9
42-262 Poczesna

Product:	Laminated glass with acoustic interlayer
Construction:	12,76 aku
Designation:	VSG (FL 6/ 0,76 PVB SC/ FL 6) kl.1/B/1
Dimension:	1230mm x 1480mm
Cross-section:	

<i>Rating</i>	R_w (C; C_{tr})	STC	OITC
<i>Basis</i>	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
<i>Value</i>	40 (-1; -3) dB	40 dB	35 dB

Łozienica, 5.12.2016


PhD Krzysztof Mech
Head of Acoustics Laboratory